

Water reducing PCE based admixture to produce free flow concrete for wide range of concrete grades

Uses

Auraflow FFC is a Water reducing superplasticiser intended for applications where water reduction and long workability retention are required.

Auraflow FFC has been designed with built-in viscosity modifying agent avoid bleeding.

- Free flow concrete,
- Pumpable concrete for shear wall construction,
- Concrete requiring long workability retention,
- High performance concrete.

Standard Compliance

Auraflow FFC complies with IS:9103-1999(2007) as water reducing admixture.

Advantages

- Suitable for producing free flow concrete for different grades of concrete
- Higher E modulus
- Improved adhesion to reinforcing and prestressing steel
- Better resistance to carbonation
- Lower permeability
- Better resistance to aggressive atmospheric conditions
- Reduced shrinkage and creep
- Increased durability

Description

Auraflow FFC is a unique combination of the latest generation superplasticisers, based on a polycarboxylic ether polymer with long lateral chains. This greatly improves cement dispersion. At the start of the mixing process an electrostatic dispersion occurs but the cement particle's capacity to separate and disperse. This mechanism considerably reduces the water demand in flowable concrete..

Auraflow FFC combines the properties of water reduction and workability retention. It allows the production of high performance concrete and/or concrete with high workability.

Technical support

Fosroc provides a technical advisory service for on-site assistance and advice on mix design, admixture selection, evaluation trials and dispensing equipment.

Properties

Appearance	:	Light yellow coloured liquid
pH	:	Minimum 6.0
Volumetric mass @ 20° C	:	1.08 kg/litre
Chloride content	:	Nil to IS:456
Alkali content	:	Typically less than 1.5 g Na ₂ O equivalent / litre of admixture.

* The uniformity parameters like specific gravity, pH, chloride content etc. will vary for specific customer requirements and mix design. Please refer our MTC issued for specific product configuration for measuring our product parameters that will be constantly and consistently administered

Dosage

The optimum dosage of Auraflow FFC to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. The normal dosage range is between 0.5 to 1.5 ltrs/100 kg of cementitious material.

Use at other dosages

Dosage outside the normal range quoted above can be used to meet particular mix requirements. Contact Fosroc for advice in these cases

Effects of overdosing

Overdosage may cause delay in the setting time and segregation.

Estimating

Packaging

Auraflow FFC is available in 200 kg drums and bulk tanker.

Storage

Auraflow FFC has a minimum shelf life of 12 months provided the temperature is kept within the range of 5°C to 50° C. Should the temperature of the product fall outside this range then contact local Fosroc office for advice.

Auraflow FFC



Precautions

Health and safety instructions

Auraflow FFC does not fall into the hazard classifications of current regulations. However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

For further information refer the Safety Data sheet available for this product.

Fire

Auraflow FFC is water based and non-flammable.

Cleaning and disposal

Spillages of Auraflow FFC should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.



FRANKLIN FLOOR TECH
OFFICE ADDRESS ADDRESS:
HOUSE# 553, SHAHINBAG, TEJGAON, DHAKA 1215, BANGLADESH.
PHONE: 01715-289292 E-MAIL:CHASHIMASUM@GMAIL.COM,
WEBSITE : WWW.FRANKLIN.COM.BD