

High range water reducing and retarding type admixture for wide range of concrete grade.

Uses

Auramix 350 DIS is a high performance super plasticizer suitable for low and high grade concrete and intended for applications where high water reduction and long workability retentions are required.

Auramix 350 DIS developed to use in:

- Long workability retention concrete.
- Pumpable Concrete.
- High performance concrete

Advantages

- Low viscosity admixture suitable for pumping different grades of concrete to greater heights.
- Suitable for concrete having cement replacements and low water cement ratio.
- Provides higher strength without increase in cement content or reduction in workability. Ideal for precast concrete production.
- Reduce rate of workability loss normally associated with super plasticiser. Reduces shrinkage cracking because of lower water cement ratio. Makes the concrete water impermeable.
- Better resistance to Carbonation.
- Reduce Shrinkage and Creep.
- Increase Durability.

Standard Compliance

Auramix 350 DIS complies to IS:9103:1999 as water reducing and retarding type admixture and ASTM C 494 Type F and G depending on dosage.

Description

Auramix 350 DIS is a unique combination of new generation super plasticizer based on polycarboxylic ether polymer with long lateral chain. Electrostatic dispersion mechanism considerably reduces the water demand in flowable concrete. It is supplied as a light brown liquid, instantly dispersible in water.

Auramix 350 DIS disperses the cement particles effectively in the concrete mix and hence exposes a larger surface area to the hydration process. This effect is used either to increase

the strength or to produce high workability concrete or reduce cement content of concrete or to retard the setting time of concrete.

Technical support

Fosroc provides technical advisory service for on-site assistance and guidance on mix design, optimum dosage evaluation of trials.

Properties

Appearance : Light Brown Liquid

pH : Minimum 6.0

Volumetric mass @ 25° C : 1.08 ± 0.02 kg / litre

Chloride content : Nil to IS:456

Workability Retention : 2 hours and more
Depending on Dosage

* The uniformity parameters like specific gravity, pH, chloride content etc. will vary for specific customer requirements and mix design. Please refer our MTC issued for specific product configuration for measuring our product parameters that will be constantly and consistently administered

Dosage

The optimum dosage of Auramix 350 DIS to meet specific requirement should always be determined by conducting laboratory and batch trials. However the normal dosage ranges between 0.3 to 1.3 percent by weight of total cement or binder content.

Dosage beyond Limits:

Dosage beyond limits can be used to meet particular mix requirements in consultation with Fosroc technical department.

Effect of over dosage:

Over dosage may cause delay in setting and segregation.

Estimating

Packaging:

Auramix 350 DIS is available in 200 kg, 250kg and bulk

Storage

Auramix 350 DIS has a minimum shelf life of 12 months provided the temperature is kept within range of 2°C and 5°C.

Auramix 350 DIS



Precautions

Health and safety instructions

Auramix 350 DIS does not fall into the hazard classifications of current regulations. However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

Fire

Auramix 350 DIS is water based and non-flammable.

Cleaning and disposal

Spillages of Auramix 350 DIS should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.

Additional information

The Fosroc range of associated products includes high strength cementitious, epoxy grout, polyester resin based mortar for rapid pre-setting of steel shims to level or for direct bedding of small base plates; Resin Anchoring systems for same day anchoring of bolts in drilled holes in concrete or rock. Also available a range of products for use in construction; viz., curing compounds, release agents, flooring systems, repair mortars, sealants and waterproofing materials.

Separate datasheets are available on these products.



FRANKLIN FLOOR TECH
OFFICE ADDRESS ADDRESS:
HOUSE# 553, SHAHINBAG, TEJGAON, DHAKA 1215, BANGLADESH.
PHONE: 01715-289292 E-MAIL:CHASHIMASUM@GMAIL.COM,
WEBSITE : WWW.FRANKLIN.COM.BD